

JOWATHERM

Packaging Hot Melt

250.00

Basis:	Polyolefin
Technical Data:	Viscosity (mPas/cPs): approx. 22,000 at 180°C (356°F) Brookfield-Thermosel Density (g/ml): approx. 0.95 (7.9 lbs./gal) Softening Point: approx. 150°C (302°F) Ring & Ball Color: yellow
Characteristics:	Elastic adhesive film, good adhesion to various substrates. The raw materials used meet requirements of the regulations or FDA 21 CFR 176.170, Subpart B.
Applications:	Tetra Pak Re Cap procedure. Especially for Tetra Cap Applicators 21 and 75. To be processed with the usual applicator systems. The substrates used and the processing conditions will influence the bonds.
Directions for use:	Application Temp: 180-200°C (356-394°F) Tested according to Jowat test methods. Customer trials are recommended.
Cleaning:	Preliminary cleaning while hot by scraping with a spatula; when cold with Jowat Cleaner 401.20.
Storage:	At least 3 years from the date of manufacture in dry and cool (15-25°C/58-76°F) conditions according to our experience.
Packaging:	In cartons of 26 lbs. net.
Marking:	None. We recommend drawing off any vapors which may form. Consult Material Safety Data Sheet.
Date Revised:	June 2001 (S)

The information contained in this leaflet is based upon our practical experience and the results of tests in our laboratory. The information contained represents average values under our test conditions. Although our testing is constantly being revised to represent the latest conditions, the information provided in this leaflet and by our free technical information service should be used only as a guide, but cannot be relied upon as a guaranty of performance or results. We strongly recommend that any user of our products conduct its own testing.

SEE THE BACK OF THIS PAGE FOR ADDITIONAL IMPORTANT INFORMATION.



Jowat Corporation
Randolph Industrial Park
P.O. Box 1368
High Point, NC 27261
Phone: (800) 322-GLUE (4583)
(336) 434-9000
Fax: (336) 434-9019
Website: www.jowat.com
Email: info@jowat.com